

Oxford Alloy® 320LR

AWS ER320LR • Stainless Steel



Key Features

❖ Used for welding base metals with similar compositions including alloy 20.

❖ Typical applications include tanks, process piping, and heat exchangers.

Conformances

AWS/ASME SFA 5.9

ER320LR

UNS N08022

Chemical Composition - As required per AWS 5.9

C	Mn	Si	Cr	Ni	Mo	Nb+Ta
0.025 max	1.5-2.0	0.15 max	19.0-21.0	32.0-36.0	2.0-3.0	8 x C min / 0.40 max
S	P	Cu				
0.02 max	0.015 max	3.0-4.0				

Mechanical Properties - As required by AWS 5.9

	Tensile Strength MPa (ksi)	Yield Strength MPa (ksi)	Elongation %
AWS Requirements	Not Specified		
Typical Results - As welded	590 (86)	400 (58)	35

Typical Welding Parameters

Diameter		Process	Volt	Amps	Shielding Gas
in	(mm)				
.035	0.9	GMAW	22-23	180-210	Spray Transfer 98% Argon / 2% Oxygen
.045	1.2	GMAW	23-25	195-260	
1/16	1.6	GMAW	25-28	260-390	
.035	0.9	GMAW	19-23	55-170	Short Circuiting Transfer 90% Helium / 7 1/2 % Argon / 2 1/2 CO ₂
.045	1.2	GMAW	19-23	100-185	
1/16	1.6	GMAW			
1/16	1.6	GTAW	14-18	90-130	100% Argon
3/32	2.4	GTAW	15-20	120-175	100% Argon
1/8	3.2	GTAW	15-20	150-220	100% Argon

Diameters & Packaging

Oxford Alloys USA			Oxford Alloys Asia Pacific		
Diameter (in)	Form	Packaging (lbs)	Diameter (mm)	Form	Packaging (kgs)
.035	GMAW	33 lb spool 1980 lb pallet	0.9	GMAW	15 kg spool 900 kg pallet
.045	GMAW	33 lb spool 1980 lb pallet	1.2	GMAW	15 kg spool 900 kg pallet
1/16	GMAW	33 lb spool 1980 lb pallet	1.6	GMAW	15 kg spool 900 kg pallet
1/16	GTAW	10 lb tube 40 lb carton	1.6	GTAW	5 kg tube 20 kg carton
3/32	GTAW	10 lb tube 40 lb carton	2.4	GTAW	5 kg tube 20 kg carton
1/8	GTAW	10 lb tube 40 lb carton	3.2	GTAW	5 kg tube 20 kg carton

Actual test results may vary. Refer test result disclaimer on page 160.